

WAKOL PU 280 Polyurethane Primer

Technical Information

Area of application

1-component reaction resin primer for

- priming absorbent and non-absorbent subfloors
- reinforcing abraded concrete edges
- blocking excessive residual moisture up to max. 6 CM% in cement screeds without floor heating
- blocking excessive residual moisture up to max. 3 CM% in cement screeds with floor heating
- blocking excessive residual moisture up to max. 7% by weight in concrete indoors and outdoors.

Special properties



1)



2)

- solvent-free according to TRGS 610
- suitable for wheelchairs
- suitable on underfloor heating

1) based on the criteria of GEV (Association for Emission-controlled Laying Materials), classified as EMICODE EC1 PLUS R: very low in emissions

2) Emission class according to French law

Technical data

Raw material base:	polyurethane resin
Drying time:	approx. 40 - 50 minutes, at least 2 hours for quartz-containing layers
Cleaning agent:	WAKOL RV 105 Neoprene Dilution, in fresh condition
Storage time:	12 months in tightly sealed containers
Storage temperature:	not below +5°C, sensitive to frost
GISCODE:	RU1
EMICODE according to GEV:	EC1 PLUS R

Application and consumption³⁾:

WAKOL 100 - 150 g/m² at only one application as primer
Primer roller,
velour or
foam roller

WAKOL 250 - 350 g/m² at double or triple application as moisture barrier
Primer roller,
velour or
foam roller

3) Consumption is dependent on surface structure and absorbability of subfloor

Subfloors

The subfloor and the climatic conditions of the room must meet the requirements of DIN 18356 or DIN 18365. Exempt from this is only the residual humidity contents of the subfloor if WAKOL PU 280 Polyurethane Primer is being used for blocking capillary humidity.

Mechanically pretreat and thoroughly vacuum-clean calcium-sulphate-based screeds according to manufacturer's specifications or according to the currently applicable standards and codes.

WAKOL PU 280 Polyurethane Primer may only be used as moisture barrier on permanently moisture resistant subfloors and for blocking off capillary moisture.

WAKOL PU 280 Polyurethane Primer may not be used on subfloors with permanently ascending moisture and steam diffusion. The product does not replace any waterproofing of building according to DIN 18195 part 4.

Usage

Shake WAKOL PU 280 Polyurethane Primer well before using. Apply evenly with WAKOL primer roller, velour or foam roller, avoid puddles. If WAKOL PU 280 Polyurethane Primer is used as a moisture barrier, it must be applied crosswise in 2 layers. Each layer must form a thin, continuous film. After the primer has dried, but within 72 hours, carry out the direct adhesion or apply within 24 hours an adhesion bridge with WAKOL D 3045 Special Primer and trowel with Wakol Levelling Compound. For details contact our technical department.

Instead of applying the special primer, a third layer of WAKOL PU 280 Polyurethane Primer can be applied. In this case, sprinkle entire last layer with WAKOL S 28 Sprinkling Sand before primer dries. After the primer has dried, at least 2 hours, sweep and vacuum the surplus sand.

Levelling with Wakol Levelling Compounds may be done after the subfloor is completely dry. Precoated areas may be walked on after approximately 40 - 50 minutes. Wakol Polyurethane Resin Adhesives e.g. WAKOL MS 230 Parquet Adhesive, elastic, WAKOL MS 240 Parquet Adhesive, elastic, WAKOL MS 260 Parquet Adhesive, firm-elastic, WAKOL MS 250 Parquet Adhesive, elastic, WAKOL MS 290 Parquet Adhesive, WAKOL PU 210 Parquet Adhesive, WAKOL PU 215 Parquet Adhesive, WAKOL PU 225 Parquet Adhesive or WAKOL PU 270 Polyurethane Adhesive can be applied directly on the dried primer WAKOL PU 280 Polyurethane Primer within 72 hours.

P:\TI-GUELTIG\TI Bau\englisch\3640GB0110 0714 WAKOL PU 280.doc
Stand: 09.07.2014 Formular: F31TBGB, Revision: 4

page 2 of 3

Important

Do not use at temperatures below +15°C. In cold weather, warm up WAKOL PU 280 Polyurethane Primer in due time in heated room. All information is based on approx. 20°C and 65% relative air humidity.

Do not use WAKOL PU 280 Polyurethane Primer on existing floor coverings, like PVC, CV, rubber and linoleum floorings.

Low air humidities as well as higher application quantities lead to extended drying times of WAKOL PU 280 Polyurethane Primer. The surface has to be non-adhesive before conducting further operations.

During the work, it is recommended to use protecting goggles and gloves. If splashes are in the eyes, rinse with plenty of water and consult a physician. Splashes on the skin may be removed with water and soap. Cleaning must be done at once.

We guarantee the uniform high quality of our products. All data is based on tests and many years of practical experience and refers to standardised conditions. The variety of materials used and the different construction site conditions, which lie beyond our control, preclude any claims based on this data. We therefore recommend making sufficient trials. Accompanying flooring manufacturer's instructions and the currently applicable codes must be observed. In addition to these specifications the laying instructions of the covering manufacturer and the presently valid standards and information leaflets, especially the leaflet 'Polyester and Epoxy Resins' issued by the Trade Cooperative Association of the Chemical Industry obtainable from the Carl Heymanns Publishing House in Cologne must be observed. We gladly provide technical advice.

The product data sheets can be found in their latest version at www.wakol.com.

This Technical Information of 08.07.2014 supersedes all previous versions.